



Technical Information
CG-90[®] Surface Saver[®]
anticorrosive deicer

DESCRIPTION:

CG-90[®] Surface Saver[®] anticorrosive deicer is an enhanced highway deicing salt product containing a corrosion inhibitor. It is a highly effective performer that provides superior protection against salt induced corrosion of exposed metal surfaces through its corrosion inhibitor, reduced scaling of concrete surfaces due to freeze/thaw cycling, and excellent deicing capabilities. This product caused significantly less scaling on concrete than plain salt (4% solution) on marginally air-entrained concrete as measured by ASTM Standard C-672 and over 50 freeze-thaw cycles in Cargill laboratory tests. Using this product may reduce highway and bridge maintenance costs.

COMPLIANCE:

CG-90[®] Surface Saver[®] anticorrosive deicer is not approved for human or animal consumption. It is intended for use only as a chemical deicer on roadways and thoroughfares. This product complies fully with ASTM Specification D 632-99 Type 1, Grade 1.

ADDITIVES:

CG-90[®] Surface Saver[®] anticorrosive deicer contains a patented corrosion inhibitor and Magnesium Chloride which enhances deicing capability.

APPLICATION:

CG-90[®] Surface Saver[®] anticorrosive deicer should be applied at the same rate as regular highway deicing salt.

HANDLING AND STORAGE:

CG-90[®] Surface Saver[®] anticorrosive deicer requires no additional handling, equipment or labor over and above that used for regular highway deicing salt. To improve caking resistance and reduce run-off, it is recommended that the product be stored in a covered storage shed or tarped. Normal precautionary measures for the safe handling of deicers should be observed.

PACKAGING:

CG-90[®] Surface Saver[®] anticorrosive deicer is available in bulk and 2000 lb minibulk bags.

METHODS OF ANALYSIS:

Methods of analysis are taken from the ASTM designations D 632-99 and E 534-98, from SHRP H205 and from Cargill. Corrosion measured on 3% solutions of deicers according to ASTM Standard G 31-72. Test method available on request.

CHEMICAL ANALYSIS:

Component	Units	Typical	Specification
Sodium Chloride	%	76.2	
Magnesium Chloride ¹	%	22.0	
Corrosion Inhibitors	%	1.8	

SIEVE ANALYSIS:

U.S.S. Mesh	Opening Inches	Opening Microns	Typical	Specification
1/2"	0.500	12700	100	100 min.
3/8"	0.375	9525	97	-
4	0.187	4760	55	-
8	0.0937	2380	38	-
30	0.0232	590	8	15 max.

Note: Sieve analysis is reported as percent passing.

PRODUCT BENEFITS:

Minimum % protection against salt induced corrosion 90 %
Magnesium chloride component melts ice down to -25° F
Reduces surface scaling of concrete due to freeze/thaw cycling.

**PRODUCING LOCATIONS: VARIOUS LOCATIONS
ACROSS THE U.S.**

No. 7703 Revised May 2007

CARGILL DEICING TECHNOLOGY

24950 Country Club
Blvd. Ste 450
North Olmsted, OH
44070
1-800-600-7258

NOTICE: All of the above statements, recommendations, suggestions and data are based on our laboratory results, and we believe same to be reliable. Nevertheless, all such statements, recommendations, suggestions and data are made without guaranty or warranty on our part and we disclaim all liabilities and warranties, expressed or implied, (including without limitation those merchantability and fitness for a particular purpose) with respect to the same.